

Appl. No. 10/806,514
Amdt. dated 10/10/06
Reply to Office action of 7/11/06

CLAIM AMENDMENTS

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (currently amended). A connecting piece for carbon material electrodes, comprising: a carbon material electrode connecting piece body, carbon fibers in said carbon material electrode connecting piece body, said carbon fibers having oxidatively activated surfaces, and a coating added to said carbon fibers, said coating being carbonized as a carbonization product of a coating material selected from the group consisting of wax, pitch, natural resins, thermoplastic polymers, and thermosetting polymers, said carbon material electrode connecting piece body having a linear coefficient of thermal expansion of from -0.5 to $+0.1 \mu\text{m}/(\text{K}\cdot\text{m})$ in a direction parallel to a lateral surface thereof, and from 1.7 to $2.1 \mu\text{m}/(\text{K}\cdot\text{m})$ in a normal plane orthogonal thereto.

Claim 2 (original). The connecting piece according to claim 1, wherein said carbon fibers have a modulus of elasticity of from 200 to 250 GPa .

Claim 3 (cancelled).

Appl. No. 10-806,514
Amdt. dated 10/10/06
Reply to Office action of 7/11/06

Claim 4 (original). The connecting piece according to claim 1, wherein said carbon fibers have an average length of from 0.5 to 40 mm.

Claim 5 (original). The connecting piece according to claim 1, wherein a mass fraction of said carbon fibers in said connecting piece body is from 0.2 to 10%.

Claim 6 (previously presented). The connecting piece according to claim 1, wherein a mass fraction of said coating on said carbon fibers, based on a mass of said carbon fibers, is from 0.2 to 15%.

Claim 7 (original). The connecting piece according to claim 1, wherein said carbon fibers are fibers based on polyacrylonitrile.

Claim 8 (original). The connecting piece according to claim 1, wherein said carbon fibers are disposed in a form selected from the group consisting of parallel filaments, woven fabrics, layered fabrics, warp-knitted fabrics, knitted fabrics, and nonwoven fabrics.

Appl. No. 10/806,514
Amdt. dated 10/10/06
Reply to Office action of 7/11/06

Claim 9 (withdrawn - currently amended). A method of producing connecting pieces for carbon material electrodes, the method which comprises:

activating surfaces of carbon fibers by oxidation in a first step;

subsequently coating the carbon fibers with a surface coating of a coating material selected from the group consisting of wax, pitch, natural resins, thermoplastic polymers, and thermosetting polymers, to form coated fibers;

optionally treating the coated fibers at a temperature of between 750 and 1,300°C for carbonization of the coating;

mixing the fibers with coke having a mean particle size in a range from 0.05 to 4 mm, with pitch having a softening temperature in a range from 70°C to 150°C, and optionally with further additives, and shaping into substantially cylindrical form bodies;

carbonizing and then graphitizing the substantially cylindrical form bodies; and

turning the graphitized form bodies to form connecting pieces with threads, each connecting piece including a carbon material electrode connecting piece body having a linear

Appl. No. 10/806,814
Amtd. dated 10/10/06
Reply to Office action of 7/11/06

coefficient of thermal expansion_of from -0.5 to +0.1 $\mu\text{m}/(\text{K}\cdot\text{m})$ in a direction parallel to a lateral surface thereof, and from 1.7 to 2.1 $\mu\text{m}/(\text{K}\cdot\text{m})$ in a normal plane orthogonal thereto.

Claim 10 (withdrawn). The method according to claim 9, which comprises using carbon fibers in a form of a fiber tow comprising from 1000 to 60,000 individual filaments, and, prior to the mixing step, cutting the fibers to form short fibers having an average length of from 0.5 to 40 mm.

Claim 11 (withdrawn). The method according to claim 9, which comprises using carbon fibers in a form of heavy tow fibers comprising from 40,000 to 2,000,000 individual filaments and, prior to the mixing step, cutting the heavy tow to form short fibers having an average length of from 0.5 to 40 mm.

Claim 12 (withdrawn). The method according to claim 9, which comprises activating the carbon fibers in an aqueous bath containing an oxidizing agent.

Claim 13 (withdrawn). The method according to claim 9, which comprises activating the carbon fibers in an aqueous bath by anodic oxidation.

Appl. No. 10/806,514

Amct. dated 10/10/06

Reply to Office action of 7/11/06

Claim 14 (withdrawn). The method according to claim 9, which comprises activating the carbon fibers in a gas stream containing an oxidizing agent.

Claim 15 (withdrawn). The method according to claim 9, wherein the coating step comprises coating the activated carbon fibers in an aqueous or solvent-containing bath containing a dispersion or solution of a coating material selected from the group consisting of wax, pitch, natural resins, thermoplastic polymers, and thermo-setting polymers.

Claim 16 (withdrawn). The method according to claim 9, which comprises treating the coated carbon fibers at a temperature of from 900 to 1,200°C for carbonization of the coating.

Claim 17 (withdrawn). The method according to claim 9, wherein the mixing step comprises preparing a mixture containing for each 100 kg of coke, from 10 to 40 kg of a pitch, and from 0.2 to 20 kg of carbon fibers.

Claim 18 (withdrawn). The method according to claim 17, which comprises adding from 0.1 to 1 kg of an iron oxide pigment having a mean particle size of from 0.1 to 2 μm as a further additive.